


T45Cr5Si3 - Special steels Datasheet

T45Cr5Si3 is Alloyed Cold Work Tool Steels acc. to IS 1570-6-96, High strength, good toughness, good hardenability, good stability against overheating, Used in the manufacture of medium-speed, heavy-duty, high-strength, high-toughness parts and high-strength components. It is mostly used to manufacture various important parts with high load and high speed, such as gears, shafts, clutches, sprockets, grinding wheel shafts, bushings, bolts, nuts, etc. It is also used to manufacture parts with wear resistance and low working temperature, variable load Welded components such as high-pressure blower blades, valve plates, and non-corrosive pipes. welding and riveting structural parts working under vibration load, such as high-pressure blower blades, valve plates and high-speed and high-load shafts, gears, sprockets, clutches, bushings, bolts, nuts, etc.

Chemical Composition



+86 - 13880247006

Tensile strength σb (MPa): $\geq 1620(165)$

Yield strength σ s (MPa): \geq 1275(130)

Elongation $\delta 5$ (%): ≥ 9

Reduction of area ψ (%): \geq 40

Impact energy Akv (J): \geq 31

Impact toughness value αkv (J/cm2): \geq 39(4)

Sample size: sample

Physical Properties

Heat Treatment

Quenching: 950°C for the first time, 890°C for the second time, oil cooling; tempering 230°C, air cooling, oil cooling; 880 ° C isothermal quenching at 280 ~ 310 ° C.



Welding Properties

Machining Properties

Similar or Equivalents Steel Grade

